

GRAYWALL™ WATERPROOFING

PRODUCT SPECIFICATIONS

COMPOSITION: Polymer emulsion, applied membrane

COLOR: Gray

DENSITY: 6.8-7.8 lbs. / gallon

MINIMUM TEMP FOR APPLICATION: 15°F

APPLICATION: Airless spray

APPLICATION RATE: Poured wall or parged block: 30-40 sq ft/gallon

PROPERTY	TEST METHODS	TEST RESULTS
Elongation	ASTM D412 (die C)	1400+%
Low-Temp Flexibility	Bend around 0.5" mandrel	Flexible to -20°F
Asphalt Content	GPC	0.0%
180 Degree Peel Adhesion	Metal plate	18 lbs/inch
Liquid Water Absorption	ASTM D95	Less than 0.5%
Resistance to Bacteria	ASTM D42 99-83 (modified)	No attack
Resistance to Degradation	ASTM E-154 (soil prep.)	Excellent
Resistance to Algae	ASTM G2975 (modified)	No attack
Resistance to Fungus	ASTM D2020 (modified)	No attack