

PANTHER™ WATERPROOFING

PRODUCT SPECIFICATIONS

COMPOSITION: Polymer modified asphalt liquid applied membrane

COLOR: Black

SOLIDS: 62% by weight

DENSITY: 8.1 lbs/gal

THICKNESS: 60 mils wet, 40 mils cured

MINIMUM TEMP FOR APPLICATION: 40°F

APPLICATION: Airless spray

APPLICATION RATE: 25-30 sq ft/gal

PROPERTY	TEST METHODS	RESULTS
Water Vapor Performance	ASTM E96	.121 perms
Elongation	ASTM D412	1900%
Low Temp Flex	Bend around .5" mandrel	pass
Crack Bridging Ability	ASTM C836	pass
Tensile Strength	ASTM C412	16.6 psi
Adhesion to Concrete	ASTM C836	49.332 lb/in