

# Rub-R-Wall Aqua Mastic

**COMPOSITION:** Single component, elastomeric compound.

**COLOR:** Green

**APPLICATION:** Apply directly with a putty knife or bulk gun at 30 to 40 mils thick.

## TECHNICAL DATA

<u>PROPERTY</u>	<u>TEST METHOD</u>	<u>RESULTS</u>
Elongation	ASTM D412	1,300 %
Peel Adhesion	ASTM D903	28 lbs/inch
Hydrostatic Head Pressure	ASTM D751	57 ft. max
Pliability @ 25°F	ASTM E1970	Pass
Solids		78 %

**PACKAGING:** 5 Gallon Pails

**LIMITATIONS:** Rub-R-Wall Aqua Mastic is UV stable but should be covered within 6 months.

Do not let product freeze.